

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **09114380 A**

(43) Date of publication of application: **02.05.97**

(51) Int. Cl.

G09F 3/04
B29C 61/06
B32B 27/28
B32B 27/30
// B29K 25:00
B29L 9:00

(21) Application number: **07275418**

(22) Date of filing: **24.10.95**

(71) Applicant: **FUJI SEAL CO LTD**

(72) Inventor: **YOSHII TOSHIYA**
WAKATSUKI TOMOHIRO
HARADA HIROSHI

(54) **HEAT SHRINKABLE LABEL**


(1)

(57) Abstract:

PROBLEM TO BE SOLVED: To provide a heat shrinkable label which shrinks less of itself, is stiff and tough and is well finished.

SOLUTION: This label is formed of an intermediate layer A consisting of a polystyrene or high-impact polystyrene resin of $\leq 10\text{wt}\%$ butadiene content and outer layers B, C which consist of a styrene-butadiene block copolymer or styrene-butadiene-acrylic acid block copolymer and are formed on both surfaces of this intermediate layer A. The thickness of the intermediate layer A is 40 to 80% of the overall thickness. The label has a heat shrinkable film 1 of 1.580 to 1.584 in the refractive index in the longitudinal direction X when the label is mounted at an adherend 3.

COPYRIGHT: (C)1997,JPO



(2)

